



Garlast® 9075 Perfluoroelastomer

Overview

Garlast® 9075 has excellent chemical corrosion resistance, including organic and inorganic acids, alkalis, esters, ethers, and ketones, aldehydes, superheated water and water vapor, etc. The maximum service temperature is 230°C and the minimum service temperature is -30°C

Garlast® 9075 is suitable for use in low temperature applications.

Garlast® 9075 can be processed into O-rings, diaphragms, gaskets, rubber strips, adhesive plates and customized products.

Application Equipment

- Mechanical seals
- Pumps
- Valves
- Compressors
- Centrifuges
- Metering and control instrumentation
- Reactors
- Agitators and grinders
- Analytical instruments
- Spraying equipment

Color

Black

Mechanical properties

Hardness ¹	Shore A	75
100% constant tensile stress ²	MPa	4.3
Tensile strength ²	MPa	16.7
Elongation at break ²	%	257
Compression set deformation ³ , 70h×204°C	%	30

1. ASTM D2240
2. ASTM D412, 500mm/min
3. ASTM D395B, 214-O-RING

Chemical media resistance

Chemical media	Media resistant grade
Aromatic hydrocarbon-based / aliphatic hydrocarbon-based oils	++++
Acid	++++
Alkali	++++
alcohol	++++
Aldehyde	++++
Amine	+++
Ether	++++
esters	++++
Ketones	++++
Superheated water, water vapor	++++
Strong oxidant	++
Ethylene oxide / propylene oxide	+++
Hot air	+++

- ++++ = Excellent
- +++ = Good
- ++ = Fair
- + = Poor
- × = N/A